

Test method (Area Normalization)

LOT.NO	Appearance	Assay	Water	Melting Point	Terephth -alic acid	Ash	Benzoic acid	Quantity
	White-or-pale yellow flake	99.00%	0.20%	178.0~182℃	0.30% max	0.10%	0.30%max	kg
	White flake	99.69	0.03	179.4	0.09	0.01	0.20	
	White flake	99.71	0.03	179.5	0.09	0.01	0.19	
	White flake	99.68	0.02	179.3	0.08	0.01	0.20	
	White flake	99.69	0.03	179.6	0.08	0.01	0.19	
	White flake	99.70	0.03	179.5	0.10	0.01	0.16	
	White flake	99.67	0.03	179.6	0.08	0.01	0.20	

Conclu
ard

Manufa
C,2024

Expiry Date:DEC,2026